Corrosivity Tests Summary

COOPER TESTING LABORATORY

CTL # _____ **Date:** _____ **Tested By:** PJ **Checked:** PJ

Client: _____ **Project:** _____ **Proj. No:** _____

Remarks:

Sample Location or ID			Resistivity @ 15.5 °C (Ohm-cm)			Chloride	Sulfate		pH	ORP (Redox)		Sulfide	Moisture	
			As Rec.	Min	Sat.	mg/kg	mg/kg	%				Qualitative	At Test	Soil Visual Description
						Dry Wt.	Dry Wt.	Dry Wt.		E_H (mv)	At Test	by Lead	%	
Boring	Sample, No.	Depth, ft.	ASTM G57	Cal 643	ASTM G57	ASTM D4327	ASTM D4327	ASTM D4327	ASTM G51	ASTM G200	Temp °C	Acetate Paper	ASTM D2216	
DH-2	-	25	-	-	-	-	44	0.0044	-	-	-	-	16.1	Olive Gray SAND w/ Silt
DH-2	-	50	-	-	-	-	533	0.0533	-	-	-	-	25.1	Olive Gray Sandy SILT
DH-3	-	15	-	-	-	-	394	0.0394	-	-	-	-	5.2	Olive Gray SAND w/ Silt
DH-3	-	85	-	-	-	-	509	0.0509	-	-	-	-	29.1	Olive Gray Sandy SILT